

Our reference: FRIM 394/490/5/4 KIL 22 (39)

Date: November 18, 2014

TEST REPORT

Job No.: 70 / 14 amendment	Page 1 of 2
This report consists of 2 pages	
This report is neither a certificate of stability nor an approval certificate. This report only covers samples supplied by the customer to be tested at FRIM. Wood Composite Testing Laboratory is not responsible in the selection of samples for testing. This report or any part of it cannot be published or used for any other purposes except with the permission from FRIM.	

CUSTOMER

Name and Address: INOVAR INDUSTRIES SDN. BHD.
Lot 2994, Jalan Bukit Badong
45600 Bestari Jaya
Selangor Darul Ehsan


SAMPLE DESCRIPTION

Material Identity: INOVAR BAMBOO FLOORING
Dimension: 50 mm x 150 mm (22 pieces)
(preparation of test samples was done by customer)

Note: The remaining of samples will be disposed after testing has been carried out.

TEST METHOD

Tested for: Formaldehyde emission
Standard test method: JIS A 5908:2003 (Particleboard)
Date of formaldehyde determination: September 10 – 11, 2014



Our reference: FRIM 394/490/5/4 Klt. 22 (60)

Date: November 18, 2014


TEST REPORT


Job No.: 70 / 14 amendment	Page 2 of 2
This report consists of 2 pages	
This report is neither a certificate of quality nor an approval certificate. This report only covers samples supplied by the customer to be tested at FRIM. Wood Composite Testing Laboratory is not responsible in the selection of samples for testing. This report or any part of it cannot be published or used for any other purposes except with the permission from FRIM.	

TEST RESULTS

Table 1: Formaldehyde value

Sample	Formaldehyde emission value (mg/L)
INOVAR BAMBOO FLOORING	Below 0.1

Prepared by

 Rozaida Latip
 Assistant Research Officer

Approved by

 Dr. Rafiqzah Rusli
 Research Officer